



Paraffine für PVC Verarbeitung



Paraffine für PVC Verarbeitung

<i>Sasol Wax</i>	<i>Erstarrungs-</i> <i>punkt</i>	<i>Ölgehalt</i> <i>(%)</i>
	DIN ISO 2207 ASTM D 938	DIN ISO 2908 ASTM D 721
5555 (flüssig oder Pulver)	55 - 57°C	0,5% max
5603 (flüssig, Tafel oder Pulver)	56 - 58°C	0,5% max
5803 (flüssig, Tafel oder Pulver)	58 - 60°C	0,5% max
7040 (flüssig oder Pulver)	68 - 72°C	-
7330 (flüssig oder Pulver)	56 - 58°C	0,5% max
8775 (flüssig oder Pulver)	76 - 80°C	-

The content on this Sasol Wax web site is proprietary to Sasol Wax and only for general information and use. In particular the content does not constitute any form of legal or others advice, recommendation or arrangement by Sasol Wax (which includes its divisions, affiliates, joint ventures or departments) or its associated information providers, and is not intended to be relied upon by users in making (or refraining from making) any specific investment or other decisions. Appropriate expert advice should be obtained before making any such decision or using the information for any specific purpose.